



# Sublimation Magnetic Materials

## Processing Instructions

Temperature 170°C

Pre-press back for 3 seconds

Pre-press front for 3 seconds

Press with white side facing heat for 150 seconds

[www.megauk.com/sublimation](http://www.megauk.com/sublimation)

01223 893900