



Sublimation Magnetic Materials

Processing Instructions

Temperature 170°C

Pre-press back for 3 seconds

Pre-press front for 3 seconds

Press with white side facing heat for 150 seconds

www.megauk.com/sublimation

01223 893900